



# TYPICAL PHYSICAL PROPERTIES OF OWENS CORNING PRODUCTS

INNOVATIONS FOR LIVING.™

Property (units)	ASTM Method	Celfort® 200 <sup>(2)</sup> Cel-Lok® System	CodeBord™	Celfort® 300	Foamular® 200	Foamular® 350	Foamular® 400	Foamular® 600	Foamular® 1000
THERMAL RESISTANCE <sup>(1)</sup> (ft <sup>2</sup> hr °F/BTU) (m <sup>2</sup> °C/W)	C 518 or C 177	5.0 0.87	5.0 0.87	5.0 0.87	5.0 0.87	5.0 0.87	5.0 0.87	5.0 0.87	5.0 0.87
COMPRESSIVE STRENGTH, min. <sup>(3)</sup> (psi) (kPa)	D1621	20 140	20 140	30 210	20 140	35 240	40 275	60 415	100 690
WATER ABSORPTION, max. (% by volume)	D2842	0.70	0.70	0.70	0.70	0.70	0.60	0.55	0.50
WATER VAPOUR PERMEANCE, max. (perms) (ng/Pa.s.m <sup>2</sup> )	E 96	0.85 49	0.85 49	0.60 35	0.85 49	0.60 35	– –	– –	– –
WATER CAPILLARITY	–	None	None	None	None	None	None	None	None
WATER AFFINITY	–	Hydrophobic	Hydrophobic	Hydrophobic	Hydrophobic	Hydrophobic	Hydrophobic	Hydrophobic	Hydrophobic
FLEXURAL STRENGTH, typical (psi) (kPa)	C 203	44 300	44 300	54 375	44 300	60 415	75 517	85 586	174 1200
LINEAR COEFFICIENT OF THERMAL EXPANSION (in/in/°F) (mm/mm/°C)	D696	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>	3.5 × 10 <sup>5</sup> 6.3 × 10 <sup>2</sup>
DIMENSIONAL STABILITY, max. (% linear change)	D2126	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
MAXIMUM OPERATING TEMPERATURE (°F) (°C)	– –	165 74	165 74	165 74	165 74	165 74	165 74	165 74	165 74

<sup>(1)</sup> Thermal resistance for 1 inch (25mm) thickness

<sup>(2)</sup> Celfort® 200 and Cel-Lok® System have the same properties

<sup>(3)</sup> At 10% deformation or yield

## Keith Wilson

Owens Corning Canada,  
Technical Services Manager  
Phone: 1-800-988-5269  
Fax: 1-800-989-8298

Hydrovac® is a trademark of Owens Corning.  
Celfort®, Cel-Lok® and CodeBord™ are trademarks of **OC Celfortec Inc.**  
Foamular® is a trademark of Owens Corning.

Manufactured by **OC Celfortec Inc.** an Owens Corning Company.

© 2003 Owens Corning. All rights reserved. INNOVATIONS FOR LIVING™ is a trademark of Owens Corning.

Pub. no. 30011292  
February 2003



INNOVATIONS FOR LIVING.™

Standard Sizes <sup>(1)</sup>	Celfort® 200	Celfort® 200 Cel-Lok®	CodeBord™	Celfort® 300	Foamular® 200 <sup>(2)</sup>	Foamular® 350 <sup>(2)</sup>	Foamular® 400	Foamular® 600	Foamular® 1000 <sup>(3)</sup>
1" x 24" x 96"	X			X	X		X	X	
1½" x 24" x 96"	X	X		X	X	X	X	X	
2" x 24" x 96"	X	X		X	X	X	X	X	X
2½" x 24" x 96"	X			X	X	X			
3" x 24" x 96"	X			X	X	X	X	X	
4" x 24" x 96"	X			X	X	X	X		
1" x 48" x 96" or 108"			X						
1½" x 48" x 96" or 108"			X						
2" x 48" x 96" or 108"			X						
CAN/ULC-S701 <sup>(4)</sup>	Type 3	Type 3	Type 3	Type 4	Type 3	Type 4	Type 4	Type 4	Type 4
CCMC Evaluation No.	11246-L	11246-L	11246-L	11247-L	11246-L	12094-L			

<sup>(1)</sup> Enquiries on non-standard sizes are welcome

<sup>(2)</sup> Standard sizes for Foamular® 200 and 350 are thickness by 24" x 48"

<sup>(3)</sup> Board width for Foamular® 1000 is 22"

<sup>(4)</sup> Replaces CAN/CGSB-51.20-M

## NOTES

- 1. Certified Performance – OC Celfortec Inc.** will provide test certification for published physical properties pertaining to our Celfort® and Foamular® products.
- 2. Jobsite Handling** – To protect Celfort® and Foamular® insulations and to prevent discolouration and/or surface deterioration caused by excessive exposure to direct sunlight, it is recommended that in exterior applications, the product be covered as soon as practicable.
- 3. Vapour Retarders** – Assemblies should be evaluated for effectiveness and location of vapour retarders to avoid condensation and subsequent damage to structures. Vapour retarders shall be chosen and applied in accordance to applicable Codes for desired assembly.
- 4. Air and Water Infiltration** – All air and water infiltration requirements for a designed assembly shall conform to applicable Building Codes.
- 5. Flame Spread Classification** – ULC flame spread classification of greater than 25 and less than 500 according to CAN/ULC-S102.2 (tunnel floor test).
- 6. Warning - Combustible** – Celfort® and Foamular® insulations are combustible and can be a fire hazard if improperly used or installed. Though they contain a flame retardant to inhibit ignition they will ignite if exposed to fire of sufficient intensity. Do not expose them to open flame or other ignition sources during shipping, handling, storage, installation or use.
- 7. Interior Protection** – When used in buildings for human occupancy, Celfort® and Foamular®

insulations must be protected by a minimum ½" (12.7mm) thick gypsum board, or approved equal, covering surfaces exposed after installation. Boards must be mechanically fastened in place as prescribed by the applicable Building Code.

- 8. Adhesives/Sealants** – Some of these products contain solvents that attack polystyrene insulation. Consult manufacturer to verify the chemical compatibility of solvents/sealants with Celfort® and Foamular® insulations.
- 9. Chemicals** – Celfort® and Foamular® insulations have good chemical resistance to many acids, caustics, salts, cements and mortars and poor resistance to some hydrocarbons and a number of other petroleum derivatives. Be sure to check with the supplier of the item regarding chemical compatibility.

**Notice:** We trust the information given herein will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Please read all statements, recommendations or suggestions in conjunction with out conditions of sale which apply to all materials supplied by us. We shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of our material is not in accordance with our current printed instructions or for other than their intended use. Our liability is expressed limited to replacement of defective goods. Any claim shall be deemed waived unless made to us in writing within thirty (30) days from the date when the basis for it was, or reasonably should have been, discovered.